



Shell Diala S4 ZX-IG OEM Bulk

- Extra Performance
- Meets IEC 60296 - Higher Oxidation Stability and Low Sulphur content

Premium Inhibited Gas Absorbing Electrical Insulating Oil

Shell Diala S4 ZX-IG is an electrical insulating oil from Shell designed to meet the gas absorbing challenges presented by specialised equipment such as high voltage instrument transformers and bushings. It offers an extended oil life with the peace of mind of zero sulphur content.

Shell Diala S4 ZX-IG is manufactured from zero sulphur base oils produced using Shell's GTL (gas-to-liquid) technology. These base oils offer a high degree of compositional consistency and have an excellent response to anti-oxidant. The product is free from PCBs, DBDS and passivators, containing only DBPC antioxidant, and a low level of aromatic hydrocarbon (for gas absorption behaviour).

Shell Diala S4 ZX-IG meets both the established and new industry copper corrosion tests.

DESIGNED TO MEET CHALLENGES

Performance, Features & Benefits

- **Extended oil life**

Shell Diala S4 ZX-IG is a fully inhibited gas absorbing oil giving outstanding oxidation performance and an extended oil life.

It has the ability to absorb gases such as hydrogen which can develop under partial discharge conditions. This makes Shell Diala S4 ZX-IG the recommended Shell product for special applications with high voltage gradients, such as bushings and instrument transformers requiring gas absorbing properties.

- **Transformer protection**

Shell Diala S4 ZX-IG is manufactured from a zero sulphur* base oil, making it intrinsically non-corrosive towards copper, without the need for passivation or other additives (apart from the DBPC antioxidant, and a low level of aromatic hydrocarbon (for gas absorption behaviour)).

Shell Diala S4 ZX-IG meets all relevant tests for copper corrosion, namely the established DIN 51353 (Silver Strip Test), ASTM D1275, and also the latest more severe tests: IEC 62535 and ASTM D1275B.

*Sulphur content below 1ppm detection limit of ASTM D5185

- **System Efficiency**

The good low temperature viscometric properties of the oil ensure proper heat transfer inside the transformer, even from very low starting temperatures.

Specifications, Approvals & Recommendations

- IEC 60296 (2012): Table 2 Transformer Oil (I) (Inhibited Oil) Section 7.1 ("Higher oxidation stability and low sulphur content")

For a full listing of equipment approvals and recommendations, please consult your local Shell Technical Helpdesk.

Typical Physical Characteristics

Properties	Method	IEC Table 2 + section 7.1 minimum	IEC Table 2 + section 7.1 maximum	Shell Diala S4 ZX-IG OEM Bulk Typical
Appearance	IEC 60296	Clear, free from sediment and suspended matters		Complies
Density @20°C kg/m ³	ISO 3675		895	806
Kinematic Viscosity @40°C mm ² /s	ISO 3104		12	9.4
Kinematic Viscosity @-30°C mm ² /s	ISO 3104		1800	381
Flashpoint P.M. °C	ISO 2719	135		158
Pour Point °C	ISO 3016		-40	-42
Neutralisation value mg KOH/g	IEC 62021-1		0.01	0.01

Properties		Method	IEC Table 2 + section 7.1 minimum	IEC Table 2 + section 7.1 maximum	Shell Diala S4 ZX-IG OEM Bulk Typical
Total Sulphur Content	mg/kg	ASTM D5185		500	1
Corrosive Sulphur		DIN 51353	Not corrosive		Not corrosive
Potentially Corrosive Sulphur		IEC 62535	Not corrosive		Not corrosive
Corrosive Sulphur		ASTM D1275 B			Not corrosive
Breakdown Voltage Untreated	kV	IEC 60156	30		70
Breakdown Voltage After Treatment	kV	IEC 60156	70		78
Dielectric Dissipation Factor @90°C	DDF	IEC 60247		0.005	0.001
Gassing Tendency	mm ³ /min	IEC 60628 A	No general requirement		-5
Oxidation Stability	500h / 120°C	IEC 61125 C	Section 7.1 Limits		
Total Acidity	mg KOH/g	IEC 61125 C		0.3	0.02
Sludge	%m	IEC 61125 C		0.05	0.05
Dielectric Dissipation Factor @90°C	DDF	IEC 61125 C		0.05	0.001
Water Content (Bulk)	mg/kg	IEC 60814		30	17
2-Furfural and related compounds content	mg/kg	IEC 61198	Not detectable		Complies
Metal passivator additives	mg/kg	IEC 60666	Not detectable		Complies
Oxidation inhibitor content (DBPC)	%mass	IEC 60666	0.08	0.4	0.2
PCA Content	% mass	IP 346		3	Complies
PCB Content	mg/kg	IEC 61619	Not detectable		Complies

These characteristics are typical of current production. Whilst future production will conform to Shell's specification, variations in these characteristics may occur.

Health, Safety & Environment

• Health and Safety

Shell Diala S4 ZX-IG is unlikely to present any significant health or safety hazard when properly used in the recommended application and good standards of personal hygiene are maintained.

Shell Diala S4 ZX-IG is free from polychlorinated biphenyls (PCB).

Avoid contact with skin. Use impervious gloves with used oil. After skin contact, wash immediately with soap and water.

Guidance on Health and Safety is available on the appropriate Safety Data Sheet, which can be obtained from <http://www.epc.shell.com>

• Protect the Environment

Take used oil to an authorised collection point. Do not discharge into drains, soil or water.

Additional Information

• Storage precautions

The critical electrical properties of Shell Diala are easily compromised by trace contamination with foreign material. Typically encountered contaminants include moisture, particles, fibres and surfactants. Therefore, it is imperative that electrical insulating oils be kept clean and dry

It is strongly recommended that storage containers be dedicated for electrical service and include air-tight seals. It is further recommended that electrical insulating oils are stored indoors in climate-controlled environments.

• Advice

Advice on applications not covered here may be obtained from your Shell representative.